DESCRIPTION

C3712, Engraving brass, are 60/40 alpha-beta brasses with different levels of lead added to give free machining properties. They are widely used for engraved plates and plaques, builders hardware, gears. They should not be used for acid etched work, for which the single phase alpha brasses should be used.

CHEMICAL COMPOSITION

Elements	Min (%)	Max (%)	
Cu	58.00	62.00	
Pb	0.25	1.20	
Fe+Sn	Hillie III BAJIII -	0.80	
Zn	Remainder		

MECHANICAL PROPERTIES ACCORDING TO EN12164 (AS PER TEMPER R410)

Ran	ige (Inch)	From	То	UTS Min (Mpa)	PS Min	Elongation Min (%)	Hardness Min	Hardness Max
Ro	und (Dia)	6.00	75.00	315.00	GP-JTH	15.00	711/2	us ille
₩ H	lex (A/F)	6.00	70.00	315.00	-	15.00	100 m	ahillin -
Sq	uare (A/F)	6.00	60.00	315.00	- [11]	15.00	obligg -	-
Rectang	gle (Thickness)	6.00	50.00	315.00	125	15.00	-	A - 18

PHYSICAL PROPERTIES

	Melting Point - Liquidus°F	1650
	Melting Point - Solidus°F	1630
1000	Densitylb/cu in. at 68°F	0.304
	Specific Gravity	8.41
	Electrical Conductivity% IACS at 68°F	27
9	Thermal ConductivityBtu/ sq ft/ ft hr/ °F at 68°F	9 69
	Coefficient of Thermal Expansion 68-57210 ⁻⁶ per °F (68 – 572°F)	11.6
	Specific Heat CapacityBtu/ lb /°F at 68°F	0.09
	Modulus of Elasticity in Tensionksi	15000
	Modulus of Rigidityksi	5600

FABRICATION PROPERTIES

Technique	Suitability
Soldering	Excellent
Brazing	Good
Oxyacetylene Welding	Not Recommended
Gas Shielded Arc Welding	Not Recommended
Coated Metal Arc Welding	Not Recommended
Spot Weld	Not Recommended
Seam Weld	Not Recommended
Butt Weld	Fair
Capacity for Being Cold Worked	Fair
Capacity for Being Hot Formed	Excellent
Machinability Rating	70

TYPICAL USES

> Industrial