## **DESCRIPTION**

CW614N, Free cutting brass, is a significantly improved form of 60/40 brass, with excellent free cutting properties. It is used in the mass production of brass components where maximum output and longest tool life are required, and where no further cold forming after machining is required.

### CHEMICAL COMPOSITION

Elements	Min (%)	Max (%)
Cu	57.00	59.00
Pb	2.50	3.50
Fe	15 Mer. Statistic - 18th	0.30
Sn	piliti - Aliz de	0.30
Ni di	E SETTLE - SHEETHE HAVE	0.30
Al	- 18 TH	0.05
Total Others	· .5 .16.	0.20
Zn	Rema	inder

# MECHANICAL PROPERTIES ACCORDING TO EN12164 (AS PER TEMPER R430)

Range (mm)	From	То	UTS Min (N/mm²)	PS Min (N/mm²)	Elongation (%)	Hardness Min	Hardness Max
Round (Dia)	2.00	40.00	430.00	220.00	10.00	- HE THE	- 6 th
Hex (A/F)	3.00	35.00	430.00	220.00	10.00	Hilling - biggs	-
Square (A/F)	3.00	35.00	430.00	220.00	10.00	-	s - 6
Rectangle (Thickness)	3.00	40.00	430.00	220.00	10.00	,5 . d	The - Hillie

## PHYSICAL PROPERTIES

Melting Point - Liquidus°F	1630
Melting Point - Solidus°F	1610
Densitylb/cu in. at 68°F	0.306
Specific Gravity	8.47
Electrical Conductivity% IACS at 68°F	28
Thermal ConductivityBtu/ sq ft/ ft hr/ °F at 68°F	71
Coefficient of Thermal Expansion 68-57210 <sup>-6</sup> per °F (68 – 572°F)	11.6
Specific Heat CapacityBtu/ lb /°F at 68°F	0.09
Modulus of Elasticity in Tensionksi	14000
Modulus of Rigidityksi	5300
VIII 70, 10, 10, 10, 10, 10, 10, 10, 10, 10, 1	

## **FABRICATION PROPERTIES**

Technique	Suitability			
Soldering	Excellent			
Brazing	Good			
Oxyacetylene Welding	Not Recommended			
Gas Shielded Arc Welding	Not Recommended			
Coated Metal Arc Welding	Not Recommended			
Spot Weld	Not Recommended			
Seam Weld	Not Recommended			
Butt Weld	Fair			
Capacity for Being Cold Worked	Poor			
Capacity for Being Hot Formed	Excellent			
Machinability Rating	90			

## TYPICAL USES

- > Architecture
- > Builders Hardware
- > Consumer
- > Industrial
- > Ordnance