Cz109

LEAD FREE BRASS

DESCRIPTION

CZ109 is a lead free material which is however quite suitable for machining due to its structural constitution. CZ109 can be therefore used as a cost-effective replacement for conventional lead-containing machining brass provided that it must not meet high requirements as regards mechanical properties and corrosion resistance

000

CHEMICAL COMPOSITION

Elements	Min (%)	Max (%)				
Cu	59.00	62.00				
Pb		0.10				
Total Others	and the second	0.30				
Zn	Remainder					

MECHANICAL PROPERTIES ACCORDING TO BS2874 (AS PER TEMPER M)

Range (mm)	From	То	UTS Min (N/mm²)	PS Min	Elongation Min (%)	Hardness Min	Hardness Max
Round (Dia)	6	40	340	5 - 8	25	- ¹	-6
Hex (A/F)	6	40	340	- 3	25		-
Square (A/F)	6	40	340	2	25		1 - 4
Rectangle (Thickness)	6	40	340	- ,5	25	- 1	-



RAJHANS METALS PRIVATE LIMITED

Cz109

LEAD FREE BRASS

PHYSICAL PROPERTIES

Melting Point - Liquidus°F	1660
Melting Point - Solidus°F	1650
Density lb/cu in. at 68°F	0.303
Specific Gravity	8.39
Electrical Conductivity % IACS at 68°F	28
Thermal Conductivity Btu/ sq ft/ ft hr/ °F at 68°F	71
Coefficient of Thermal Expansion 68-57210-6 per °F (68 - 572°F)	11.6
Specific Heat Capacity Btu/ lb /°F at 68°F	0.09
Modulus of Elasticity in Tension ksi	15000
Modulus of Rigidity ksi	5600
	Melting Point - Solidus°F Density Ib/cu in. at 68°F Specific Gravity Electrical Conductivity % IACS at 68°F Thermal Conductivity Btu/ sq ft/ ft hr/ °F at 68°F Coefficient of Thermal Expansion 68-57210-6 per °F (68 - 572°F) Specific Heat Capacity Btu/ Ib /°F at 68°F

FABRICATION PROPERTIES

Technique	Suitability
Soldering	Excellent
Brazing	Excellent
Oxyacetylene Welding	Good
Gas Shielded Arc Welding	Fair
Coated Metal Arc Welding	Not Recommended
Spot Weld	Good
Seam Weld	Not Recommended
Butt Weld	Good
Capacity for Being Cold Worked	Fair
Capacity for Being Hot Formed	Excellent
Forgeability Rating	90
Machinability Rating	40
198	

TYPICAL USES

- > Architecture
- > Builders Hardware
- > Fasteners
- > Industrial

