DESCRIPTION

CW609N, Free cutting brass, is a significantly improved form of 60/40 brass, with excellent free cutting properties. It is used in the mass production of brass components where maximum output and longest tool life are required, and where no further cold forming after machining is required.

CHEMICAL COMPOSITION

Elements	Min (%)	Max (%)
Cu line	57.00	59.00
Pb	3.50	4.20
Fe INS	JE HE I CANADA - RIV	0.30
Sn	This is	0.30
_{III} E Ni ALTH	E MENTS - LINE MIT BANK	0.30
HART AI	MEAL HAR - RATH	0.05
Total Others	- 15 ME	0.20
Zn Jahren	Rema	inder

MECHANICAL PROPERTIES (AS PER TEMPER R430)

Range (mm)	From	То	UTS Min (N/mm²)	PS Min	Elongation (%)	Hardness Min	Hardness Max
Round (Dia)	2.00	40.00	430.00	250.00	10.00	all the	- 614 JL
Hex (A/F)	3.00	40.00	430.00	250.00	10.00	TUIL - BUT	-
Square (A/F)	3.00	40.00	430.00	250.00	10.00	_	e - (E)
Rectangle (Thickness)	3.00	40.00	430.00	250.00	10.00	.55	The - This

PHYSICAL PROPERTIES

Melting Point - Liquidus°F	1630
Melting Point - Solidus°F	1610
Densitylb/cu in. at 68°F	0.306
Specific Gravity	8.47
Electrical Conductivity% IACS at 68°F	28
Thermal ConductivityBtu/ sq ft/ ft hr/ °F at 68°F	₅ 71
Coefficient of Thermal Expansion 68-57210-6 per °F (68 – 572°F)	11.6
Specific Heat CapacityBtu/ lb /°F at 68°F	0.09
Modulus of Elasticity in Tensionksi	14000
Modulus of Rigidityksi	5300

FABRICATION PROPERTIES

Technique	Suitability			
Soldering	Excellent			
Brazing	Good			
Oxyacetylene Welding	Not Recommended			
Gas Shielded Arc Welding	Not Recommended			
Coated Metal Arc Welding	Not Recommended			
Spot Weld	Not Recommended			
Seam Weld	Not Recommended			
Butt Weld	Fair			
Capacity for Being Cold Worked	Poor			
Capacity for Being Hot Formed	Excellent			
Machinability Rating	90			

TYPICAL USES

- Architecture
- **Builders Hardware**
- Consumer
- Industrial
- Ordnance